CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No.: TC- 5548

Format No: CP/TF/01

TEST REPORT OF FINE AGGREGATE

ID	:	CP-2018-09-06-01 **Date: 10-09-18**
tomer	:	Assistant Executive Engineer, Yelahanka Sub Division, BBMP, Bangalore.
lress	:	Yelahanka Sub Division, BBMP, Bangalore.
ject Name	:	Construction of Compound wall to Indira Canteen in Ward No.02 of Yelahanka Sub Division
gency	:	Technical Manager(West), Karnataka Rural Infrastructure Development Limited (KRIDL), BBMP, Bangalore.
ustomer's Reference	:	BBMP/EE(YNK.D)/W.O/000020/2018-19
ource of Sample	:	Sample supplied by Agency
ample Condition	:	Satisfactory
Date of Receipt	:	06-09-18
Sample ID No	:	2018-09-06-01 /03
Sample Type	:	Fine Aggregate
Reference to BIS codes	:	IS 383 : 2016 (Specification for Coarse and fine Aggregates) IS: 2386 :1963(Part - 1, 3) RA2012 IS 2386 Part 1: Particle Size and Shape IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption
Date of test	:	06-09-18
Total weight taken	:	1000 grams

Sl.no	Sieve Size	Weight Retained (gms)	Cumulative Weight Retained (gms)	% Cumulative Weight Retained	% Passing	Requirement as per IS 383:2016			
						Grading Zone I	Grading Zone II	Grading Zone III	Grading Zone IV
1	10 mm	0	0	0.0	100.0	100	100	100	100
2	4.75 mm	21	21	2.1	97.9	90-100	90-100	90-100	95-100
3	2.36 mm	185	206	20.6	79.4	60-95	75-100	85-100	95-100
4	1.18 mm	201	407	40.7	59.3	30-70	55-90	75-100	90-100
5	600 micron	168	575	57.5	42.5	15-34	35-59	60-79	80-100
6	300 micron	229	804	80.4	19.6	5-20	8-30	12-40	15-50
7	150 micron	153	957	95.7	4.3	0-10	0-10	0-10	0-15
8	Pan	43	1000	100.0	0.0	---	---	---	---

Result :The tested Sample Conforms to Grading Zone II

CIVIL Pro Sig..... Date..... BANGALORE

AE-dl

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No.: TC- 5548

Format No. CP/TF/01

TEST REPORT OF PHYSICAL PROPERTIES OF CEMENT - 53 Grade

Lab ID	:	**CP-2018-09-06-01** **Date: 10-09-18**
Customer	:	Assistant Executive Engineer, Yelahanka Sub Division, BBMP, Bangalore.
Address	:	Yelahanka Sub Division, BBMP, Bangalore.
Project Name	:	Construction of Compound wall to Indira Canteen in Ward No.02 of Yelahanka Sub Division
Agency	:	Technical Manager(West), Karnataka Rural Infrastructure Development Limited (KRIDL), BBMP, Bangalore.
Customer's Reference	:	BBMP/EE(YNK.D)/W.O/000020/2018-19
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	06-09-18
Sample ID No	:	2018-09-06-01 /01
Sample Type	:	Birla Super 53grade
Reference to BIS codes	:	IS 12269 : 2013, 53 Grade Ordinary Portland cement Specification , IS 4031 (Part 1,2 3,4,5, 6,11):1988 IS 4031 Part 1 DETERMINATION OF FINENESS BY DRY SIEVING, Clause 4.4 IS 4031 Part 2, Determination of Fineness by Blaine Air Permeability Method, Clause 5 IS 4031 Part 3, Determination of Soundness, Clause 5,Clause 6 IS 4031 Part 4, Determination of Consistency of Standard Cement Paste, Clause 5 IS 4031 Part 5, Determination of Initial & Final Setting Time, Clause 5 IS 4031 Part 11,DETERMINATION OF DENSITY , Clause 6
Date of test	:	07-09-18
Environmental Conditions during test	:	Temperature: 26°C Humidity: 72%

SLNo.	Physical properties	Results	Requirement as per IS 12269: 2013
1	Fineness by dry sieving (%)	1.95	–
2	Finess by Air permeablity method (m^2/kg,Min)	285.4	225m^2/kg, Min
3	Density (gm/cc)	3.12	–
4	Standard Consistency (%)	29.5%	Not specified
5	Initial Setting time	145 minutes	Not less than 30 minutes
6	Final Setting time	240 minutes	Not more than 600 minutes
7	Soundness (Le Chatelier's Method)	1.5mm	Not more than 10 mm

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

AE-2

AE-02

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL Pro Sig..... Date..... BANGALORE

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

CIVIL PRO

AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005

4, 7TH MAIN MALLESWARAM, BANGALORE -3

Certificate No.: TC- 5548

Format No: CP/TF/01

TEST REPORT OF PHYSICAL PROPERTIES OF CEMENT - 53 Grade

Date: 14-09-18

Lab ID	:	CP-2018-09-06-01
Customer	:	Assistant Executive Engineer, Yelahanka Sub Division, BBMP, Bangalore.
Address	:	Yelahanka Sub Division, BBMP, Bangalore.
Project Name	:	Construction of Compound wall to Indira Canteen in Ward No.02 of Yelahanka Sub Division
Agency	:	Technical Manager(West), Karnataka Rural Infrastructure Development Limited (KRIDL), BBMP, Bangalore.
Customer's Reference	:	BBMP/EE(YNK.D)/W.O/000020/2018-19
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	06-09-18
Sample ID No	:	2018-09-06-01 /01
Sample Type	:	Birla Super 53grade
Reference to BIS codes	:	IS 12269 : 2013, 53 Grade Ordinary Portland cement Specification , IS 4031 Part 4, Determination of Consistency of Standard Cement Paste, Clause 5 IS 4031 Part 6, Determination of Compressive Strength, Clause 6
Date of test	:	07-09-18
Environmental Conditions during test	:	Temperature: 26°C Humidity: 72%

Compressive Strength

Sl.No.	Physical properties	Results	Requirement as per IS 12269: 2013
1	3 Days	29.5N/mm^2	Not less than 27 N/mm^2
2	7 Days	39.5N/mm^2	Not less than 37 N/mm^2

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

AE-2

AE-01

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

CIVIL Pro BANGALORE Sig..... Date.....

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

TESTING LABORATORY | STRUCTURAL

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No.: TC- 5548

Format No: CP/TF/01

TEST REPORT ON COARSE AGGREGATES

Lab ID	:	**CP-2018-09-06-01** **Date: 10-09-18**
Customer	:	Assistant Executive Engineer, Yelahanka Sub Division, BBMP, Bangalore.
Address	:	Yelahanka Sub Division, BBMP, Bangalore.
Project Name	:	Construction of Compound wall to Indira Canteen in Ward No.02 of Yelahanka Sub Division
Agency	:	Technical Manager(West), Karnataka Rural Infrastructure Development Limited (KRIDL), BBMP, Bangalore.
Customer's Reference	:	BBMP/EE(YNK.D)/W.O/000020/2018-19
Source of Sample	:	Sample supplied by Agency
Sample condition	:	Satisfactory
Date of Receipt	:	06-09-18
Sample ID No	:	2018-09-06-01 /02
Sample Type	:	40mm down size coarse aggregate
Reference to BIS codes	:	IS: 383:2016 (Specification for Coarse and fine Aggregates) IS: 2386 :1963(Part - 1,3,4) RA2011 IS 2386 Part 1: Particle Size and Shape IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption IS 2386 Part 4: Mechanical Properties
Date of test	:	06-09-18

SIEVE ANALYSIS (PARTICLE SIZE DISTRIBUTION) OF 40MM DOWN COARSE AGGREGATE:

Total weight taken : 15000 grams

Sample No.	Sieve No.	Weight Retained in gms	Cumulative Weight Retained in gms	% Cumulative Weight Retained	% Passing	Required as per IS 383:2016
1	80 mm	0	0	0.0	100	100
2	40 mm	244	244	1.6	98.4	90-100
3	20 mm	5432	5676	37.8	62.2	30-70
4	10 mm	4332	10008	66.7	33.3	10-35
5	4.75 mm	4654	14662	97.7	2.3	0-5
6	Pan	338	15000	100.0	0	---

AE-02

CIVIL PRO Sig.....